



## A NEW FORCE IN CHEMICAL MANUFACTURING

Unit 2, 14-16 Lee Holm Road  
St Marys NSW 2760  
Australia

Ph: 1300 738 250 (Australia)  
Ph: +61 2 9833 9766 (International)  
Fax: 02 9623 3670

sales@chemtools.com.au  
www.chemtools.com.au

# TECHNICAL DATA SHEET

SEPTEMBER 2014

## PRODUCT NAME

8577 Medium Strength Thread Sealant

## PRODUCT RANGE

Part Number	Available Size
8577-50	50 ml
8577-250	250 ml



Refer to MSDS for product safety guidelines

## 8577 Medium Strength Thread Sealant

Chemtools® 8577 is a high performance anaerobic thread sealant designed for the locking and sealing of metal threaded pipes and fittings. The product cures rapidly in the absence of air between close fitting metal surfaces and provides low pressure resistance immediately after application.

It is ideal to seal against gases, water, LPG, hydrocarbons, oils and other chemicals. Excellent thixotropic properties prevent migration of the sealant before or during curing.

### APPLICATIONS:

- Ideal for locking and sealing of threaded metal pipes and fittings.
- Designed for coarse threads. Suitable for stainless steel surfaces without the need of surface activation.

### ADHESIVE PROPERTIES:

Composition	Methacrylate Ester
Appearance	Yellow
Viscosity @25°C (Brookfield RVT Spindle 3 @ 20 rpm)	24,000 - 80,000 cps
Specific Gravity	1.09
Flash Point	> 100°C
Solvent Content	None
Shelf Life	1 Year

### CURING PROPERTIES:

Handling Cure Time	10 - 30 minutes
Functional Cure Time	2 - 4 hours
Full Cure Time	24 hours
Temperature Range	-50 to 80°C
Compressive Shear Strength - (ISO 10123) Steel Pins & Collars	5 N/mm <sup>2</sup> (725 psi)

Torque - ISO 10964

Breakaway	M10 steel nuts and bolts	11 Nm, 100 lb.in
Prevail	M10 steel nuts and bolts	6 Nm, 50 lb.in
Break Loose (Pre-torqued to 5 Nm)	M10 steel nuts and bolts	17 Nm, 150 lb.in
Max. Prevail (Pre-torqued to 5 Nm)	M10 steel nuts and bolts	17 Nm, 150 lb.in

**PHYSICAL PROPERTIES:**

Coefficient of Thermal Expansion, ASTM D696, K <sup>-1</sup>	80 x 10 <sup>-6</sup>
Coefficient of Thermal Conductivity, ASTM C177, W/m.K	0.10
Specific Heat, kJ/kg.K	0.30

**CHEMICAL RESISTANCE PROPERTIES:**

Chemical	Temperature	% Initial Strength Retained	
		500 hours	1000 hours
Acetone	22°C	80	65
Ethanol	22°C	100	95
Motor Oil	125°C	100	100
Petrol	22°C	100	100
Brake Fluid	22°C	100	95
Water/Glycol	87°C	90	90

**APPLICATION INSTRUCTIONS:**

Surfaces should be dry, clean, and free of any contamination. Apply 360° bead of product to the leading threads of the male fitting, leaving the first thread free. Force the material into the threads and voids, adjust product amount accordingly and apply a 360° bead of product on the female threads also. Assemble and tighten as required.

**STORAGE:**

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at a room temperature between 7°C to 28°C. Please do not return any unused material to its original container.

**PRECAUTIONS:**

This product is capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the material.

**WARRANTY:**

All products purchased from or supplied by Chemtools® are subject to terms and conditions set out in the contract. Chemtools® warrants only that its products meet the specifications designated as such herein, or in other publications. All other information supplied by Chemtools® is considered accurate, but is furnished upon the express condition. The customer shall make its own assessment to determine the products suitability for a particular purpose. Chemtools® makes no other warranty, either expressed or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or products will not infringe any patent.